


TEST REPORT

TRUE CRAFT COTTON PLAINS - RH1

Applicant: Mr J. Bank
 Oddies Textiles
 Unit 3, Bank House
 Greenfield Road
 Colne
 Lancashire
 BB8 9NL

	MTS Lab Reference:	39093006
	Report Date:	23/10/19
	Number of Samples:	5
	Received on:	30/09/19
	Condition received:	Supplied without packaging visibly undamaged condition.

RH1 Bright pink, Baltic, Lime, Hot Tomato, Amethyst fabrics

Reference is made in this report to chromium VI analyses carried out by a sub-contractor laboratory. This testing is outside the scope of UKAS accreditation.

RESULTS

EN 71-3:2013+A3:2018 Migration of certain elements	PASS
--	-------------

Prepared by G. S. Kirkland

Date: 23rd October, 2019

Signature: *G. Kirkland*

Authorised on behalf of MTS

by G. S. Kirkland, Lab Manager

Date: 23rd October, 2019

Signature: *G. Kirkland*

Page 1 of 3 pages.

This report is issued in accordance with MTS (UK)'s terms and conditions which are available on request.

Modern Testing Services (UK) Limited

Modern Testing Services (UK) Limited, 118 Lupton Avenue, Leeds, LS9 6ED, UK

Tel (44) 0844 556 5596 / 0113 240 7011 Fax: (44) 0113 240 9350 Email: info@mts-uk.co.uk Website: www.mts-uk.co.uk

Registered Company 7337435

VAT Registration Number: 997452852

EN 71-3:2013+A3:2018 Migration of certain elements**Category III - Scraped off material****PASS**

The EN 71-3 screening test used by MTS (UK) tests for the migration of 16 of the 19 'elements' restricted by EN 71-3:2013+A3:2018;

Please note that a new chromium VI limit of 0.053 mg/kg, imposed by EU Directive 2018/725 will come into force on 18 November 2019, applicable to toys which are placed on the market from this date. This has been applied to the samples tested; if inapplicable, this can be reverted to the previous limit of 0.2 mg/kg on request.

It does not test for the presence of chromium III, chromium VI or organic tin specifically, it does however test for chromium and tin and compliance with the limits for chromium III, chromium VI or organic tin may be inferred from low results from these analyses (see below).

- A. "Amethyst" textile
- B. "Baltic" textile
- C. "Lime" textile
- D. "Bright pink" textile
- E. "Hot tomato" textile

The material(s) complied with the limits of the 16 elements specifically analysed for (see analysis table).

The migration of tin from the sample(s) was determined to be not greater than 4.9 mg/kg, which, when expressed in the form of tributyl tin, would not be greater than the organic tin limit of 12 mg/kg, the material(s) can therefore be inferred as complying with the organic tin limit.

The migration of chromium from samples A and B was greater than the chromium VI limit of 0.053 mg/kg, the material required specific chromium VI migration analysis to determine compliance with the chromium VI limit, this was carried out by a sub-contractor and was found to comply with the limit.

The migration of chromium from the remaining samples was not greater than the chromium VI limit of 0.053 mg/kg, the materials can therefore be inferred as complying with the chromium VI limit.

The migration of chromium from the sample was not greater than the chromium III limit of 460 mg/kg, the material can therefore be inferred as complying with the chromium III limit.

~~~End of page~~~

Method of test: EN 71-3:2013+A3:2018 Migration of certain elements

ANALYSIS RESULTS

Category 3

Date of test: 04/10/19

Samples marked \* were sieved, those marked # were centrifuged. Details of additional acid required to lower pH and solvent used for extraction appear in [ ] in sample description.  
 Deviations from standard method: pH of conventional polymers and textiles not checked; samples only filtered if required to prevent ICP blockages.  
 Solid to acid extractant ratio exceeded 1:50 with sample weights below 100 mg and when additional acid was used to lower pH.  
 Quantities of soluble metals determined by inductively coupled plasma spectroscopy.  
 Test results marked ^ are within the area to which uncertainty of measurement applies & compliance/non-compliance cannot be inferred.

| Metals | Al    | Sb  | As | Ba    | B     | Cd | Cr      | Co  | Cu   | Pb | Mn    | Hg | Ni  | Se  | Sr    | Sn     | Zn    |
|--------|-------|-----|----|-------|-------|----|---------|-----|------|----|-------|----|-----|-----|-------|--------|-------|
| Limits | 70000 | 560 | 47 | 18750 | 15000 | 17 | 460.053 | 130 | 7700 | 23 | 15000 | 94 | 930 | 460 | 56000 | 180000 | 46000 |

|                | Wt (Mg) |   |       |        |     |     |     |         |     |     |     |     |     |     |     |     |       |     |
|----------------|---------|---|-------|--------|-----|-----|-----|---------|-----|-----|-----|-----|-----|-----|-----|-----|-------|-----|
| A              | 214     | 3 | < 0.5 | < 0.05 | < 5 | < 5 | < 1 | 0.221   | < 5 | < 5 | 1.0 | < 5 | < 1 | < 5 | < 5 | < 5 | < 1.0 | < 5 |
| B              | 212     | 4 | < 0.5 | < 0.05 | < 5 | < 5 | < 1 | 0.079   | < 5 | < 5 | 0.9 | < 5 | < 1 | < 5 | < 5 | < 5 | < 1.0 | < 5 |
| C              | 212     | 3 | < 0.5 | < 0.05 | < 5 | < 5 | < 1 | 0.016   | < 5 | < 5 | 0.6 | < 5 | < 1 | < 5 | < 5 | < 5 | < 1.0 | < 5 |
| D              | 202     | 2 | < 0.5 | < 0.05 | < 5 | < 5 | < 1 | < 0.001 | < 5 | < 5 | 0.3 | < 5 | < 1 | < 5 | < 5 | < 5 | < 1.0 | < 5 |
| E              | 223     | 5 | < 0.5 | < 0.05 | < 5 | < 5 | < 1 | 0.002   | < 5 | < 5 | 0.3 | < 5 | < 1 | < 5 | < 5 | < 5 | < 1.0 | < 5 |
| END OF SAMPLES |         |   |       |        |     |     |     |         |     |     |     |     |     |     |     |     |       |     |

