

Our Ref: SW/LS/RM

03 February 2018

Report 313537

Page 1 of 2

Oddies Textiles
Unit 3 Bank House
Greenfield Road
Colne
Lancashire
BB8 9NL

DATE RECEIVED	:	29 JANUARY 2018
QUALITY REFERENCE	:	A-01684-2800-F01 JOB F159510
REPUTED FIBRE CONTENT	:	100% NYLON
FABRIC DESCRIPTION	:	MESH
COLOUR/DESIGN	:	GREY
ORDER NUMBER	:	LD240118-2

REQUEST: Flammability Assessment (Based on EN 71-2)





S. WISEMAN
LABORATORY DIRECTOR



L.SHERIDAN
LABORATORY MANAGER

This report shall not be reproduced except in full without the written approval of HSTTS. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

*This test has been sub-contracted

Our Ref: SW/LS/RM

03 February 2018

Report 313537

Page 2 of 2

EN 71-2 Flammability Assessment

PASS

The net textiles was tested to clause 5.4 to assess its suitability for use against requirements 4.3 (disguise costumes) of EN71-2:2011.

There were no washing instructions or advice not to wash the item accompanying the toy so samples were washed in water in accordance with the method specified in this standard. The samples were then line dried.

The rate of spread of flame of the materials should not exceed 30 mm/sec over a 500 mm distance. If the rate of spread of flame is between 10 mm/sec and 30 mm/sec a warning would be required on both the toy and its packaging.

Where possible, samples were cut with the length corresponding to the vertical direction of the toy when in use, as this is unknown, samples were taken in both the length and width directions from the material supplied.

Where possible, samples of 610 by 100 mm of each material were taken, otherwise two samples of 310 mm by 100 mm were taken and tested as one.

Sample Size	Orientation	Result
Grey net Full size	'Length'	0 mm/sec
Grey net Half sizes	'Width'	0 mm/sec

The materials would all be suitable for use as main materials in a worn toy or costume.