


Technical data sheet

ACT.
2263

- Good quick-flowing
- Low viscosity
- Extensively used in the apparel industry
- Good bonding and washing resistance on various substrates



GENERAL INFORMATION

Chemical information	Copolyamide	
Form	WEB	
Standard Colour	White	
Backing possibility	On paper	
	<i>Min.</i>	<i>Max.</i>
Weight (gsm) (According ISO 12127)	8	50
Tolerance	+/-1,5g(<16gsm) or +/-10%(≥16gsm)	+/-1,5g(<16gsm) or +/-10%(≥16gsm)

PHYSICAL DATA

	<i>Min</i>	<i>Max</i>
DSC melting range ⁽¹⁾ (°C)	100	110
DSC Onset ⁽¹⁾ (°C)	87	
Viscosity (MVR) ⁽²⁾ @ 160°C	Very low	
	<i>(very high < 2cc/10min; high = 3 to 18; medium = 19 to 50; low = 51 to 100; very low >100)</i>	
Physical note	Based on caprolactame free raw material	

⁽¹⁾According to ISO 11357, ⁽²⁾According ISO 1133-1; Measured at 160°C, 2,16kg

FINAL PRESENTATION (see our quality standard)

Maximum Width (mm)	1500
Width tolerance (mm)	Untrimmed: +0;+10 / Trimmed: depending on the width
Standard roll length (lm)	500 depending on weight
Remark	-
Storage conditions	Do not store below 0°C or above 40°C. Store in a dry place away from direct sunlight. Shelf life: 12 months after delivery under appropriate storage conditions and into its original packaging