


Technical data sheet

ART.

1152

- Good quick-flowing adhesion
- Low viscosity
- Low heat process
- Extensively used in the apparel industry



GENERAL INFORMATION

Chemical information	Copolyamide	
Form	NET	
Standard Colour	Milky white	
Backing possibility	With or without paper backing	
	<i>Min.</i>	<i>Max.</i>
Weight (gsm) (According ISO 12127)	30	30
Tolerance	+/-1,5g(<16gsm) or +/-10%(≥ 16gsm)	+/-1,5g(<16gsm) or +/-10%(≥ 16gsm)

PHYSICAL DATA

DSC melting range ⁽¹⁾	<i>Min</i>	<i>Max</i>
	107	117
DSC Onset ⁽¹⁾	98	
Viscosity (MVR) ⁽³⁾	Very low	
	<i>(very high < 2cc/10min; high = 3 to 18; medium = 19 to 50; low = 51 to 100; very low > 100)</i>	
Physical note	-	

⁽¹⁾According to ISO 11357. ⁽²⁾According ISO 527-1, on samples from 20 to 30µm thick and 50mm wide. Not measured on web and net. ⁽³⁾Measured at 160°C, 2,16kg (According ISO 1133-1); Some of the products may overlap on 2 types. ⁽⁴⁾Only for TPU.

FINAL PRESENTATION (see our quality standard)

Maximum Width (mm)	1500
Width tolerance (mm)	Untrimmed: +0;+10 / Trimmed: depending on the width
Standard roll length (lm)	100
Remark	-
Storage conditions	Do not store below 0°C or above 40°C. Store in a dry place away from direct sunlight. Shelf life: 12 months after delivery under appropriate storage conditions and into its original packaging